



Fabric Specification Sheet

Style: Apagòn Style IV

Available Width: 72" (182.8 cm)

Roll Length: 30-yard standard (27 Meters)

Shipping: Rolls shipped on 3" (7.62 cm) ID paper core

Construction: 3 ply (49.1% Vinyl, 33.4% Fiberglass, 17.37% Proprietary Coating)
(Each vinyl is equal thickness and weight)

Surface Texture: Back side laminated with color coated front side

Thread Count: 59 threads per square inch
(23 per square centimeter)

Weight: 12.2 ounces (+ or - 2.0)
(406.8 grams/m²) (+ or - 68)

Thickness: 12.2 mil (+ or - 2.0)
(.31 millimeters) (+ or - .05)

Instron Tear Strength: Warp 15.8 Lbs/In Fill 10.98 Lbs/In


Instron Breaking Strength: Warp 289.74 Lbs/In Fill 327.81 Lbs/In

Opacity: Blackout
Visual check

Washability: Material may be dusted with a damp cloth. When scrubbing is necessary, warm water, mild detergents and gentle rubbing are recommended.

Flammability: National Fire Protection Association Standard 701-2019 Test Method 1

Other Tests Passed: AATCC Test Method 16-3 – Colorfastness to Light
ASTM D3335 85a - Lead Testing
ASTM Method G-21-15 – Resistance to Fungi
UL GreenGuard Gold Certified
ASTM C423 – Sound Absorption (NRC Rating 0.05 – SAA Rating 0.05)
AATCC Test Method 30-2013 – Fungal Growth
(Trichoderma virens – ATCC #9645)
(Aspergillus niger – ATCC #6275)
ISO 22196:2011 – Antibacteria (Staphylococcus aureus – ATCC #6538)



8/2020

MAILING ADDRESS
P.O. Box 1017
Warsaw, IN 46581

STREET ADDRESS
102 Enterprise Drive
Warsaw, IN 46580

PHONE
(574) 269-1280

FAX
(574) 269-7747

E-MAIL
Mail@indianacoatedfabrics.com

WEBSITE
www.indianacoatedfabrics.com