

Fabric Specification Sheet

Style:	Apagòn Style III	
Available Width:	98" (249 cm)	
Roll Length:	30-yard standard (27 Meters)	
Shipping:	Rolls shipped on 3" (7.62 cm) ID paper core	
Construction:	3 ply (62.1% Vinyl, 31.6% Fiberglass, 6.2% Proprietary Coating) (Each vinyl is equal thickness and weight)	
Surface Texture:	Back side laminated with color coated front side	
Thread Count:	59 threads per square inch (23 per square centimeter)	
Weight:		+ or - 2.0) + or - 68)
Thickness:		+ or - 2.0) + or05)
Instron Tear Strength:	Warp Fill 17.13 Lbs/In 11.43 Lbs	s/In
Instron Breaking Strength:	Warp Fill 298.26 Lbs/In 299.72 Lbs/In	
Opacity: Visual check Washability:	Blackout	
	Material may be dusted with a damp cloth. When scrubbing is necessary, warm water, mild detergents and gentle rubbing are recommended.	
Flammability:	National Fire Protection Association Standard 701-2019 Test Method 1	
Other Tests Passed:	AATCC Test Method 16-3 – Colorfastness to Light ASTM D3335 85a - Lead Testing ASTM Method G-21-15 – Resistance to Fungi UL GreenGuard Gold Certified ASTM C423 – Sound Absorption (NRC Rating 0.05 – SAA Rating 0.05) AATCC Test Method 16 – Colorfastness to Light AATCC Test Method 30-2013 – Fungal Growth (Trichoderma virens – ATCC #9645) (Aspergillus niger – ATCC #6275) ISO 22196:2011 – Antibacteria (Staphylococcus aureus – ATCC #6538)	
	ANTIMICROBIAL	



8/2020

MAILING ADDRESS P.O. Box 1017 Warsaw, IN 46581 (574) 269-1280

PHONE

STREET ADDRESS 102 Enterprise Drive Warsaw, IN 46580

WEBSITE www.indianacoatedfabrics.com

FAX (574) 269-7747

E-MAIL Mail@Indianacoatedfabrics.com